



PCT/EP 00/07910

10/069321

#2

INVESTOR IN PEOPLE

EP00107910

**PRIORITY EJU
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

REC'D 21 DEC 2000	
WIPO	PCT


I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.


Signed *Andrew Gersey*
Dated 23 November 2000



THIS PAGE BLANK (USPTO)

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)



The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

1. Your reference

P1999S004

2. Patent application number

(The Patent Office will fill in this part)

17 AUG 1999

9919490.4

3. Full name, address and postcode of the or of each applicant (underline all surnames)

EXXON RESEARCH AND ENGINEERING COMPANY
PO BOX 390
FLORHAM PARK
NEW JERSEY 07932
UNITED STATES OF AMERICA

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

DELAWARE, USA

439836003 ✓

4. Title of the invention

STABILIZED LUBRICATING FORMULATION AND METHOD

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

FLETCHER WATTS, Susan Jane
SOMERS, Harold Arnold
ESSO ENGINEERING (EUROPE) LTD
PATENTS AND LICENCES, MAILPOINT 70
ESSO HOUSE ERMYN WAY
LEATHERHEAD
SURREY KT22 8XE

Patents ADP number (if you know it)

436030004 ✓

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

YES

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description 15

Claim(s) 3

Abstract 1

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77) 2

Request for preliminary examination and search (Patents Form 9/77) 1

Request for substantive examination (Patents Form 10/77)

Any other documents

(please specify)

1 Fee Sheet

11. I/We request the grant of a patent on the basis of this application.

Signature

HAROLD ARNOLD SOMERS

Date 17 AUG 99

12. Name and daytime telephone number of person to contact in the United Kingdom

TRICIA LEMPRIERE
01372 223777

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks before and in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

REFERENCE No. P1999S004

INVENTORS : David Gary Lawton HOLT

TITLE : STABILIZED LUBRICATING FORMULATION AND METHOD

APPLICANT : EXXON RESEARCH AND ENGINEERING COMPANY

AGENT : Susan Jane FLETCHER WATTS
ESSO ENGINEERING (EUROPE) LTD
PATENTS AND LICENCES
MAILPOINT 70
ESSO HOUSE
ERMYN WAY
LEATHERHEAD
SURREY KT22 8XE
ENGLAND

THIS PAGE BLANK (USPTO)

5

STABILIZED LUBRICATING FORMULATION AND METHOD

10 This invention relates to lubricating oil based on base stocks having less than 99 wt% saturates content and containing one or more sulfur-phosphorus containing anti-wear/extreme pressure additives and one or more hindered phenol anti oxidants which combination are prone to crystal formation, wherein the formation of crystals is reduced or eliminated by the use of a crystallization suppressant.

15

Lubricating oils containing various antioxidants or esters or fatty acid amides or sulfur-phosphorus additives in combination with phenols are known in the literature.

20

U.S. Patent 5,167,844 is directed to a formulation comprising a base oil, at least one sulfur phosphorus containing compound, at least one amine and at least one hindered phenol.

25

JP 07034078 is directed to a hydraulic oil comprising mineral oil with an aromatic content of up to 1.5 wt% and a phenolic and aminic anti-oxidant, an alkenyl succinic acid imide rust inhibitor and a phosphoric acid type anti wear agent.

30

U.S. Patent 5,580,483 is directed for lubricating a refrigeration system compressor using a break-in lubricating oil which is an ester type oil. Additionally an adipate, phthalate, azelate, sebacate, trimellitate can also be present as well as tri hydrocarbyl phosphate, corrosion inhibitors such as alkali and/or alkaline earth metal sulfonate, antioxidants such as aminic or phenolic antioxidants and metal deactivators such as triazoles.

5

WO 97/14776 is directed to hydraulic oils comprising base oils combined with an amine antioxidant, a phenolic antioxidant, a phosphate ester and a fatty acid amide and/or polyhydric alcohol ester.

10

U.S. Patent 5,773,393 is directed to a composition comprising at least 70 wt% oil of lubricating viscosity and an amount effective to inhibit metal corrosion of a soluble additive comprising (a) at least one amide compound of a mono- or polycarboxylic acid or reactive derivative thereof and (b) at least 0.5 equivalents of at least one primary or secondary amine per mole of amide provided that when (a) is an amide of a dicarboxylic acid and the amine is an alkanol amine the mixture contains more than 0.5 equivalent of the amine (b) per equivalent of the amide.

15

The present invention is directed to a lubricating oil formulation having a reduced potential for the formation of crystals comprising a major amount of a lubricating oil base stock having less than about 99 wt% saturates content, preferably less than about 98 wt% saturates content, and a minor amount of additives comprising a mixture of sulfur-phosphorus containing anti-wear/extreme pressure additive, hindered phenol antioxidant and one or more high molecular weight di-, or polycarboxylic acid, anhydride or mixture thereof such as polyolefin succinic acid/anhydride, and to a method for reducing crystal formation in lubricating oil formulations comprising base oil having less than about 99 wt% saturates content, preferably less than about 98 wt% saturates content, and containing sulfur phosphorus anti-wear/extreme pressure additive and hindered phenolic anti-oxidant wherein the crystals are attributed to the interaction between the sulfur phosphorus containing anti-wear/extreme pressure agent and the hindered phenol by adding to said lubricating oil a minor effective amount of one or more high molecular weight di- or polycarboxylic acid or

25

30

- 5 anhydride such as polyolefin succinic acid/poly olefin succinic anhydride and/or mixtures thereof.

The lubricating base oil is any oil of lubricating oil viscosity having less than about 99 wt% saturates content, preferably less than about 98 wt%
10 saturates content.

Lubricating oils meeting this criterion are any natural mineral or petroleum based lubricating oils derived from crude oil, tar sands, shale oil, etc., such that they contain a quantity of unsaturation resulting in a saturates content
15 of less than of 99%, or a mixture of natural mineral or petroleum based lubricating oils in combination with a base oil or oils having a saturates content of greater than 99 wt%, e.g. hydrocarbon oils such as white oils and/or severely hydrotreated, hydrocracked mineral oils, or synthetic oils such as poly alpha olefins, esters, isomerized wax or isomerized Fischer-Tropsch wax, the
20 combination or mixture of such oils being characterized as having less than about 99 wt% saturates. Saturates content, for the purposes of this specification, is a measure of the absence of aromatic species, and was determined by high pressure liquid chromatography (HPLC) according to method IP 368, except where otherwise expressly indicated.

25

The lubricating oil base stocks useful in the present invention have the typical lubricating oil viscosity, usually possessing kinematic viscosities in the range of about 1.5 to 500 mm²/s at 100°C, preferably 5 to 120 mm²/s at 100°C.

30

Mineral or petroleum based lubricating oil base stocks can be derived from paraffinic, naphthenic and mixed base crudes. Conventional refinery techniques include distillation, solvent and/or catalytic dewaxing,

- 5 solvent extraction, hydrofinishing, hydrocracking, vis breaking, deasphalting, etc.

Synthetic lubricating oils that can be used include esters of di- and tri-basic acids, reacted with linear or branched aliphatic alcohols such as C₆-C₁₅ alcohols, such as di-2-ethylhexyl sebacate, phthalic ester esters of glycols such as C₁₃ oxo acid diester or tetraethylene glycol, or complex esters such as one formed from 1 mole of sebacic acid and 2 moles of tetraethylene glycol and 2 moles of 2-ethylhexanoic acid. Other synthetic oils that can be used include synthetic hydrocarbons such as alkyl benzenes, e.g., alkylate bottoms from the alkylation of benzene with tetrapropylene, or the copolymers of ethylene and propylene; silicone oils, e.g., ethyl phenyl polysiloxanes, methyl polysiloxanes, etc.; polyglycol oils, e.g., those obtained by condensing butyl alcohol with propylene oxide; carbonate esters, e.g., the product of reacting C₆ oxo alcohol with ethyl carbonate to form a half ester followed by reaction of the latter with tetraethylene glycol, etc. Other suitable synthetic oils include the polyphenyl ethers, e.g., those having from about 3 to 7 ether linkages and about 4 to 8 phenyl groups.

Other suitable oils are the polyol ester oils made by reacting an aliphatic polyol with carboxylic acid. Aliphatic polyols contain from 4 to 15 carbon atoms and has from 2 to 8 esterifiable hydroxyl groups. Examples of polyols are trimethylolpropane, pentaerythritol, dipentaerythritol, neopentyl glycol, tripentaerythritol and mixtures thereof. The carboxylic acid reactant is selected from aliphatic monocarboxylic acid or mixtures of aliphatic mono carboxylic acids or mixtures of aliphatic mono- and di-carboxylic acids. The carboxylic acids contain 4 to 12 carbons and include straight and branched chain carboxylic acids.

5 Included in the group of synthetic oils are those recovered from tar
sands, shale oil, light hydrocarbons produced via, for example, the Fischer-
Tropsch process for converting synthesis gas (CO and hydrogen) into hydro-
carbons, wax isomerate oils produced by the catalytic hydroisomerization of
natural petroleum waxes (i.e., slack wax) or synthetic waxes (i.e., Fischer-
10 Tropsch waxes) or mixtures of such waxes. See USP 5,059,299 and USP
5,158,671 for description of wax isomerization and the oils produced thereby.
Other synthetic oils include the polyolefins such as polybutene, polyisobutenes
and especially the polyalphaolefins, i.e., fluids formed by the oligomerization of
at least one 1-alkane hydrocarbon having from 6 to 20 carbons, preferable 8 to
15 16 carbons, more preferably 8 to 12 carbons.


 Regardless of the source of the oil, for the purposes of the present
invention, the lube oil base stock, be it a single oil or a mixture of oils, is
characterized as having a saturates content of less than about 99%, preferably
20 less than 98 wt%.

 Sulfur-phosphorus containing anti-wear/extreme pressure additives
are well known in the industry, and are materials containing both sulfur and
phosphorus in the same molecule. For the purpose of the present specification,
25 and appended claims sulfur-phosphorus containing anti wear, extreme pressure
additives are those which react with hindered phenols to produce crystals. Those
skilled in the formulation art can readily determine without expenditure of
inventive effort, whether a particular sulfur-phosphorus containing anti-
wear/extreme pressure agent reacts with hindered phenol anti-oxidant to produce
30 crystals. If it does not, it is not within the scope of this invention. Any sulfur-
phosphorus containing anti-wear/extreme pressure agent which is found to react
with hindered phenol antioxidant to produce crystals in the subject base oil is
within this invention and formalities containing such agents and phenolic

- 5 antioxidants will be beneficially affected is evidenced by reduction on
elimination of crystal formation by the addition of the high molecular weigh di-
or poly carboxylic acid, anhydride or mixture thereof, as shown below, provided
such carboxylic acid, anhydride or mixture thereof is used in an amount of at
least about 0.0013 wt% for each 1 ppm phosphorus attributable to the sulfur-
10 phosphorus containing anti-wear/extreme pressure agent.

Sulfur-phosphorus anti-wear/extreme pressure additives which
interact with hindered phenols to produce crystals are exemplified by, but not
limited to, materials of the type:


15



wherein R_1 , R_2 and R_3 are independently hydrogen or hydrocarbyl provided at
least one is hydrocarbyl so as to render the material oil soluble and X is sulfur.

20


- The hydrocarbyl groups preferably contain from 1 to 40 carbons and
are aromatic and/or aliphatic groups and include aryl alkyl and alkaryl and
aralkyl and heteroatom substituted aromatic and aliphatic group, the heteroatom
substitutents being sulfur, nitrogen or oxygen substituted as such into the
25 hydrocarbon skeleton or as sulfur, oxygen or nitrogen containing moiety, e.g.,
—OR_y, —SH, —SO₂H, —N(R_y)₂, —C—R_xOR_y,



- 5 etc., and mixtures thereof substituted onto or into the hydrocarbon backbone,
wherein R_X is C_1 - C_{20} hydrocarbyl or hydrocarbylene group and R_Y is hydrogen
or a C_1 - C_{20} hydrocarbyl or hydrocarbylene.

Such sulfur-organo phosphorus containing anti-wear/extreme
10 pressure agent is typically used at a concentration sufficient to provide of from
about 2 ppm to 320 ppm phosphorus, preferably 40 ppm to 200 ppm phosphorus,
most preferably about 80 ppm to 130 ppm phosphorus.


An example of a sulfur phosphorus anti-wear/extreme pressure
15 additive which has been found to react with hindered phenols to form crystals is
a material is 2-ethylhexyl 10-ethyl-4-[[2-[(2 ethylhexyl)-oxyl]-2-oxoethyl] thio]-
7-oxo-8-oxa-3,5-dithia-4-phospha tetradecanoate, CAS # 83547-95-9. Based on
the name and the CAS number, it is believed this material has the following
structure:




20 It must be noted that for the purposes of the present invention metal
dihydrocarbyldithiophosphate (metal DDP) or ashless DDP do not fall within the
above definition of sulfur-phosphorus containing anti-wear/extreme pressure

5 additive because it has been found that they do not form crystals when combined with hindered phenols in base oils.


Hindered phenolic anti oxidants are also well known in the industry. Such materials include by way of example and not limitation 2,6-di-t-butyl
 10 phenol, 2,6-di-t-butyl alkylated phenol where the alkyl substituent is hydrocarbyl and contains between 1 and 20 carbon atoms, such as 2,6-di-t-butyl-4-methyl phenol, 2,6-di-t-butyl-4-ethyl phenol, etc., or 2,6-di-t-butyl-4-alkoxy phenol where the alkoxy substituent contains between 1 and 20 carbons such as 2,6-di-t-butyl-4-methoxyphenol; materials of the formula



where X is zero to 5, R₈ and R₉ are the same or different and are C₁-C₂₀ hydrocarbyl which may contain oxygen or sulfur or be substituted with oxygen or sulfur containing groups; and materials of the formula



where y is 1 to 4 and R₁₀ is a C₁ to C₂₀ hydrocarbyl which may contain oxygen sulfur or nitrogen or be substituted with oxygen, sulfur or nitrogen containing groups such as 2,6 di tert butyl α dimethylamino P-cresol,



wherein it is believed R_{11} is C_8C_{17} (CAS # 125643-61-0), and mixtures of such phenolic type antioxidants.

10 Preferably the phenolic anti-oxidant contains an ester group, such as in formula IV above.

Phenolic type anti oxidants are typically used at a concentration of from about 0.01 to 2.0 wt%, preferably about 0.1 to 1.0 wt%, most preferably
15 about 0.3 to 0.5 wt%, based on active ingredient.

In order to prevent or at least minimize the formation of crystals in lubricating oils based on base stock having less than 99% saturates preferably less than 98 wt% saturates and containing a mixture of sulfur-organo phosphorus
20 anti-wear/extreme pressure additive and phenolic anti-oxidant, wherein the sulfur phosphorus containing anti-wear/extreme pressure agent interacts with the hindered phenol to produce crystals a minor, crystal preventing effective amount of a high molecular weight carboxylic acid, anhydride or mixture thereof is added to the lubricating oil formulation.

25 The carboxylic acid or anhydride can be any high molecular weight acid such as di- or polycarboxylic acid, anhydride or mixture thereof of molecular weight of about 300-5000. Such acids, anhydrides or mixtures thereof include polyhydrocarbylene substituted di- or polycarboxylic acids or anhydrides
30 wherein the poly hydrocarbylene group has a molecular weight in the range 300 to 5000, preferably 750 to 2000, most preferably 900 to 1000 (e.g.,

- 5 polyisobutylene) and wherein the carboxylic group is, e.g., succinic or maleic acid, anhydride or mixture thereof.

Poly hydrocarbylenes are homopolymer or interpolymers of polymerizable olefin group containing monomers having from 2 to 16 carbons.

- 10 Interpolymers are those made using two or more different olefinic groups containing monomer including monomer such as styrenes. Poly hydrocarbylene homo and interpolymers are well known in the literature and to those skilled in the art and need not be further described herein.

- 15 Preferably the carboxylic acid or anhydride or mixture thereof used is polyalkylene succinic or maleic acid, anhydride, or mixtures thereof, most preferably polyisobutylene (PIB) succinic acid, anhydride or mixtures thereof wherein the PIB group has a molecular weight of about 900 to 1000.

- 20 Such high molecular weight carboxylic acids, anhydrides are employed in an amount in the range of about 0.0026 to 0.8 wt%, preferably about .08 to 0.4 wt%, most preferably about 0.12 to 0.24 wt%, based on active ingredients.

- 25 In general, at least 0.0013 wt% of high molecule weight carboxylic acid, anhydride or mixture thereof is used for each 1 ppm phosphorous from the sulfur-organo phosphorus anti-wear/extreme pressure agent.

EXAMPLES

30

Example 1

This example (Table 1) is presented to show that, in a base stock having a saturates content of less than 99 wt%, the combination of a sulfur-

- 5 phosphorous anti-wear/extreme pressure agent with a hindered phenol results in crystal formation while the combination of a sulfur free phosphate extreme pressure agent and hindered phenol does not result in crystal formation.

TABLE 1

					Crystals at 3 months
Base oil (1)	+	.55 wt% sulfur-phosphorus extreme pressure agent (2)	+	0.4 wt% hindered phenol (3)	yes
Base oil (1)	+	.4 wt% hindered phenol	+	.55 wt% sulfur free phosphate EP agent (4)	no

10

(1) solvent refined base oil, about 88% saturates 150 SN oil

(2) sulfur phosphorus extreme pressure agent CAS #83547-95-9 which is 60% sulfur-phosphorus component active ingredient (also contained C₄-C₈ diphenyl amine as balance of additive)

15 (3) 100% active ingredient, CAS # 125643-61-0

(4) 100% active ingredient, isopropylated triaryl phosphate

The resulting lubricant had a phosphorus content of 120ppm by weight, measured according to standard test ASTM D5185-97, attributable to the sulphur-phosphorus extreme pressure agent (which was the sole phosphorus-containing component contained in the lubricant formulation)

20

Example 2

This example (Table 2) is presented to show that crystal formation is eliminated in formulations normally exhibiting crystal formation by the addition of high molecular weight anhydride but that crystal formation is not eliminated by the addition of high molecular weight anhydride-poly amine dispersant, or by the addition of esters. All formulations tested in this example further contained typical pour point depressants, anti-rust agent and an amino para cresol antioxidant.

25

30

TABLE 2

Base oil (1)	+ .55 wt% sulfur-phosphorus EP agent (2)	+ 0.4 wt% hindered phenol (3)	+	Crystals at 3 months	
					yes
(“)	(“)	(“)	+	PIBSA + PAM (4)	yes
(“)	(“)	(“)	+	Esters (5)	yes
(“)	(“)	(“)	+	PIBSA (6)	yes
(“)	(“)	(“)	+	PIBSA (7)	no

(1) Base oil, a 50/50 mixture of 150 N (88% saturates) and 400 N (about 78% saturates).

(2) See Table 1.

(3) See Table 1.

(4) PIBSA-PAM was tested at concentration of from 0.05 to .4 wt% and at all concentrations used crystals formed within the three month time period of the test.

(5) Esters tested were di iso nonyl phthalate at 0.05 to 4 wt%; di iso-tridecyl adipate at .1 to .5 wt%; C₆ and C₁₃ phthalate at .5 wt%. None were effective at eliminating crystal formation during the three month time period of the test.

(6) PIBSA is polyisobutylene succinic anhydride, having a polyisobutylene molecular weight of 950. When used at .04 wt% and .08 wt% active ingredient level, it did not eliminate crystal formation.

(7) PIBSA (of note 6) at .16 wt% and .32 wt% active ingredient level eliminated crystal formation.

5

Example 3

10 This example (Table 3) is presented to show the effect of base stock
saturation on the suppression of crystal formation when using PIBSA in
combination with sulfur phosphorus extreme pressure agent and hindered
phenol.

TABLE 3

	+	0.55 wt% sulfur phosphorus extreme pressure agent (2)	+	0.4 wt% hindered phenol (3)	+	0.16 wt% PIBSA (4)	Crystals at 3 months
Base oil (1)							no
Base oil (5)		(“)		(“)		(“)	no
Base oil (6)		(“)		(“)		(“)	no
Base oil (7)		(“)		(“)		(“)	no
Base oil (8)		(“)		(“)		(“)	no
Base oil (9)		(“)		(“)		(“)	cloudy
Base oil (10)		(“)		(“)		(“)	cloudy
Base oil (10)		(“)		(“)		(“)	cloudy
(1) See Table 1.				(“)		PIBSA @ .8% AI	yes
(2) See Table 1.							
(3) See Table 1.							
(4) PIBSA is polyisobutylene succinic anhydride, polyisobutylene molecular weight 950.							
(5) 150 N, about 80% saturates.							
(6) 150N FDA C grade white oil about 80% saturate (by clay-gel analysis - ASTM D 2007).							
(7) Hydrocracked 90 N, about 92% saturates.							
(8) 150 N FDA A grade white oil, 100% saturates							
(9) Hydrocracked 150 N, about 99.9% saturates.							
(10) PAO-6, 100% saturates.							

- 14 -

5

From this it is seen that in base oils having less than 99% saturates and containing mixtures of sulfur-phosphorus extreme pressure agent and hindered phenol, which are prone to crystal formation, crystal formation is suppressed on adding PIBSA where as in base oils of essentially 100% saturates
10 content even addition of PIBSA failed to prevent crystal formation and even increasing PIBSA concentrate to 0.8 wt% (active ingredient) did not prevent crystal formation.

5 CLAIMS:

1. A lubricating oil of reduced crystal formation potential attributable to the interaction of sulfur phosphorus containing anti-wear/extreme pressure agents and hindered phenolic antioxidants comprising a major amount
10 of a base oil of lubricating viscosity and having less than about 99 wt% saturates content, and a minor amount of additive comprising a sulfur-phosphorus containing anti-wear/extreme pressure additive, a hindered phenol antioxidant and a high molecular weight di- or poly- carboxylic acid, anhydride or mixture thereof provided at least 0.0013 wt% high molecular weight carboxylic acid,
15 anhydride or mixture thereof is present for each 1 ppm phosphorus attributable to the sulfur phosphorus containing anti-wear/extreme pressure agent.

2. The lubricating oil of claim 1 wherein the sulfur-phosphorus anti-wear/extreme pressure agent is in an amount sufficient to provide about
20 2 ppm to 320 ppm phosphorus, the hindered phenol antioxidant is at a concentration of from about 0.01 to 2.0 wt% based on active ingredient and the high molecular weight di- or poly-carboxylic acid is at a concentration of in the range of about 0.0026 to 0.8 wt% based on active ingredient.

25 3. The lubricating oil of claim 1 or 2 wherein the sulfur-phosphorus containing anti-wear/extreme pressure agent is in an amount sufficient to provide from 40 ppm to 200 ppm phosphorus.

30 4. The lubricating oil of claim 1 or 2 wherein the sulfur-phosphorus containing anti-wear/extreme pressure agent is in an amount sufficient to provide from 80 ppm to 130 ppm phosphorus.

5 5. The lubricating oil of any preceding claim wherein the hindered phenol is at a concentration of about 0.1 to 1.0 wt% based on active ingredient.

6. The lubricating oil of claim 2, 3 or 4 wherein the hindered phenol is at a concentration of about 0.3 to 0.5 wt% based on active ingredient.

10

7. The lubricating oil of claim 2, 3 or 4 wherein the high molecular weight di- or poly-carboxylic acid, anhydride or mixture thereof is at a concentration of about 0.08 to 0.4 wt% based on active ingredient.

15 8. The lubricating oil of any preceding claim wherein the high molecular weight di- or poly-carboxylic acid anhydride or mixture thereof is at a concentration of about 0.12 to 0.24 wt% based on active ingredient.

9. The lubricating oil of any preceding claim wherein the high
20 molecular weight di- or poly-carboxylic acid, anhydride mixture thereof is a polyhydrocarbylene substituted di- or poly-carboxylic acid, anhydride or mixture thereof wherein the polyhydrocarbylene group has a molecular weight in the range 300 to 5,000.

25 10. A method for reducing crystal formation in lubricating oil containing a mixture of sulfur phosphorus anti-wear/extreme pressure agent and hindered phenols antioxidant wherein the sulfur-phosphorus anti-wear/extreme pressure agent interacts with the phenolic antioxidant to produce crystals, such method comprising adding to a major amount of a base oil of lubricating
30 viscosity having a saturates content of less than 99 wt%, a minor amount of additives comprising a sulfur-phosphorus containing anti-wear/extreme pressure agent a hindered phenol antioxidant and a high molecular weight di- or poly-carboxylic acid, anhydride or mixture thereof provided at least 0.0013 wt% of

- 5 the high molecular weight di- or poly-carboxylic acid, anhydride or mixture thereof is used for each 1 ppm phosphorus attributable to the sulfur-phosphorus containing anti-wear/extreme pressure agent.

5

ABSTRACT

STABILIZED LUBRICATING FORMULATION AND METHOD

10

Lubricating oil formulations comprising base oil, sulfur-phosphorous
anti-wear/extreme pressure agents and hindered phenol antioxidants which anti-
wear/extreme-pressure agents and hindered phenolic antioxidants are prone to
15 crystal formation wherein the base oil is characterized as having a saturates
content of less than 99% are stabilized against crystal formation by the addition
of a minor amount of a high molecular weight di- or polycarboxylic acid
anhydride, or mixture thereof.

THIS PAGE BLANK (USPTO)